

:: Elastic beige

polyester fine putty beige

CHARACTERISTICS

Elastic beige is a 2K-polyester filler developed specially for the body painter and fulfilling the highest demands of quality

- High standard of quality
- The optimum working material for the body painter.
- For use on steel surfaces only
- Not for use on zinc and aluminium surfaces.

APPLICATION

Because of its qualities of filling pores in the area of filling and base putty, this fine putty can also be used to repair small scratches and paint defects.

PRODUCT DATA

MATERIAL DATA:

- **Delivery viscosity at 20°C:** as a paste
- **VOC content:** 2004/42/IIB (b) (250) < 250g/l
- **Shade:** beige

HANDLING

BASE:

The base must be clean, dry and grease-free.

DOSING:

Addition of 2-3 % by weight hardener paste.

Overdosing of the hardener paste is to be avoided. Bleeding-through and colour changes in the finishing coat might be the result.



03/2021

POT LIFE:

Elastic beige: 3-4 minutes at + 20°C room temperature

Elastic beige slow: 5-6 minutes at + 20°C room temperature

Elastic beige very slow: 9 minutes at + 20°C room temperature

REACTION TEMPERATURE:

At least +5°C.

APPLICATION:

Spread on with a spatula

Air drying at +20°C room temperature, 15 - 20 minutes

SANDABILITY:

Following drying times given.

As filling putty

First sanding – dry with P80 - P120

Re-sanding - dry with P120 - 240

As fine putty

First sanding - dry with P120 - P180

Re-sanding - dry with P180 - P240

REWORKING:

The fine putty can be gone over with CS Spray.

STORAGE:

Ca. 6 - 8 months at 18 - 20° C in closed original container



03/2021

SAFETY ISSUES

The before mentioned technical data and information, especially the recommendations for applying and using our products, are based on our current knowledge and experience when applied under normal conditions. In practice, the materials, surfaces or site conditions are so different that no warranty regarding the working results or liability, arising out of any relationship, can be inferred neither from this information nor from a verbal consultation, except we are charged with intent or gross negligence. In this case the user is obliged to prove that he has informed us about all points required for a proper and promising judgement in writing, in time and completely. Patent rights of any third party are to be observed. Furthermore, our general sales and delivery Terms and Conditions and the latest Technical Data Sheet, which should be demanded, apply.

Directions for handling and waste disposal are in our Material Safety Data Sheet and the specifications of the Employers Liability Insurance Association for the chemical industry.